

GRIP CLAD GRP GRATINGS

ANTI-SLIP STAIR & FLOOR SURFACES

Resin System Choice of GRP Grating

Type O

Orthophthalic Polyester Resin – This type of grating can be used in the special environments of sea water, weak acid etc

Operating Temp

-50°C - 100°C

Type I

Isophthalic Polyester Resin – This type of grating can be used in the special environments of middle concentration inorganic acid, inorganic alkali etc

Operating Temp

-50°C - 105°C

Type V

Vinyl Ester Resin - This type of grating can be used in the special environments of corrosion with either acid or alkali or both.

Operating Temp

-50°C - 110°C

We can also supply grating used in food industry and those with High Fire Resistance at customers request.